

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 May 2004 (21.05.2004)

PCT

(10) International Publication Number
WO 2004/042101 A2

- (51) International Patent Classification⁷: C22C 30/00, 32/00, 19/05

(21) International Application Number: PCT/GB2003/004754

(22) International Filing Date: 4 November 2003 (04.11.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data: 0225648.5 4 November 2002 (04.11.2002) GB

(71) Applicant and

(72) Inventor: FLAHAUT, Dominique [FR/GB]; 24 The Avenue, Flat 2, Linthorpe TS5 6PD (GB).

(74) Agent: FRANKS & CO.; 9 President Buildings, Savile Street East, Sheffield S4 7UQ (GB).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:
— without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: HIGH TEMPERATURE ALLOYS

(57) **Abstract:** An improved nickel-chromium-iron alloy is provided, which comprises up to about 5 % of hafnium-containing particles. In one embodiment, an improved creep resistant castable oxide dispersion strengthened nickel-chromium-iron alloy comprises up to about 5 % of hafnium, with at least part of the hafnium being present as finely dispersed oxidised particles. Further embodiments of the improved alloy can comprise additionally up to about 15 % by weight aluminium. The alloy is particularly useful in the production of creep resistant tubes and castings, for example, for the petrochemical market.

WO 2004/042101 A2